

Pro Steel Plus

Property	Test Method	English	Metric
Color	Observed	Black	Black
Bond Method	Observed	Thermal Flatbond	Thermal Flatbond
Typical Weight	ASTM D-3776	2.7 oz/sy	90 GSM
Grab Tensile (MD)	ASTM D-5034	80 lbs	36 Kgs
Grab Tensile (CD)	ASTM D-5034	80 lbs	36 Kgs
Grab Elongation (CD)	ASTM D-5034	47 %	47 %
Trapezoid Tear	ASTM D-5733	36 lbs	16 Kgs
Flow Rate at 2% Head	ASTM D-4491	250 gpm/sf	10,186 lpm/sm

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.