

TerraGrid® TXG-5

TerraGrid® integrally formed triangle geogrids are composed of high-quality polypropylene resin and carbon black with no inclusion of postconsumer recycled materials. The punched and drawn process produces the following interrelated characteristics:

Property	Test Method	English	Metric
Rib Pitch ²	Measured	1.6 in	40 mm
Node Thickness ²	Measured	0.13 in	3.3 mm
Rib Thickness ^{2,3}	Measured	0.06 in	1.4 mm
Rib Shape	Observed	Rectangular	Rectangular
Aperture Shape	Observed	Triangular	Triangular
Junction Efficiency ⁴	ASTM D7737	95 %	95 %
Aperture Stability ⁵	ASTM D7864	8.0 kg-cm/deg	8.0 kg-cm/deg
Radial Stiffness, 0.5% Stain ⁶	ASTM D6637	27,000 lbs/ft	394 kN/m
Isotropic Stiffness Ratio ⁷	ASTM D6637	0.8	0.8
Resistance to Chemical Degradation ^{2,7}	EPA 9090A	100 %	100 %
UV Degradation Resistance ⁸	ASTM D4355	100 %	100 %

1. Unless indicated otherwise, values shown are minimum average roll values determined in accordance with ASTM D4759; descriptions of test procedures are briefly described in the following notes.
2. Nominal values
3. Average at rib-junction
4. Expressed as a comparison of ASTM D7737 strength to ASTM D6637 strength of the same sample.
5. US Army COE, modified.
6. Determined from tensile stiffness measured in any in-plane axis from testing in accordance with ASTM D6637, modified.
7. The ratio between the minimum and maximum observed values of radial stiffness at 0.5% strain, measured on rib and midway between rib directions.
8. Resistance to loss of load capacity or structural integrity when subjected to aggressive chemical environment per EPA 9090, 120 hours.
9. Resistance to loss of load capacity or structural integrity when subjected to aggressive UV light environment per ASTM D4355, 500 hours.

DISCLAIMER: Descriptions regarding the products described herein are based solely upon information provided by the manufacturer and are provided for informational purposes only. **NOTHING CONTAINED HEREIN SHOULD BE CONSTRUED AS CREATING AN EXPRESSED OR IMPLIED WARRANTY, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS, EACH OF WHICH IS HEREBY DISCLAIMED. THERE ARE NO WARRANTIES THAT EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF.** The final determination as to the suitability of any product of Hanes Geo Components in any particular application rests solely with the user. Hanes Geo Components reserves the right to alter or modify its products and descriptions at any time without notice.